

Springer Tracts in Civil Engineering

Series Editors

Sheng-Hong Chen, School of Water Resources and Hydropower Engineering,
Wuhan University, Wuhan, China

Marco di Prisco, Politecnico di Milano, Milano, Italy

Ioannis Vayas, Institute of Steel Structures, National Technical University of
Athens, Athens, Greece

Springer Tracts in Civil Engineering (STCE) publishes the latest developments in Civil Engineering - quickly, informally and in top quality. The series scope includes monographs, professional books, graduate textbooks and edited volumes, as well as outstanding PhD theses. Its goal is to cover all the main branches of civil engineering, both theoretical and applied, including:

- Construction and Structural Mechanics
- Building Materials
- Concrete, Steel and Timber Structures
- Geotechnical Engineering
- Earthquake Engineering
- Coastal Engineering; Ocean and Offshore Engineering
- Hydraulics, Hydrology and Water Resources Engineering
- Environmental Engineering and Sustainability
- Structural Health and Monitoring
- Surveying and Geographical Information Systems
- Heating, Ventilation and Air Conditioning (HVAC)
- Transportation and Traffic
- Risk Analysis
- Safety and Security

Indexed by Scopus

To submit a proposal or request further information, please contact:

Pierpaolo Riva at Pierpaolo.Riva@springer.com (Europe and Americas) Wayne Hu at wayne.hu@springer.com (China)

More information about this series at <https://link.springer.com/bookseries/15088>

Androniki Miltiadou-Fezans ·
Theodosios P. Tassios

Mix-Design and Application of Hydraulic Grouts for Masonry Strengthening

 Springer

Androniki Miltiadou-Fezans
School of Architecture
National Technical University of Athens
Athens, Greece

Theodosios P. Tassios
School of Civil Engineering
National Technical University of Athens
Athens, Greece

ISSN 2366-259X ISSN 2366-2603 (electronic)
Springer Tracts in Civil Engineering
ISBN 978-3-030-85964-0 ISBN 978-3-030-85965-7 (eBook)
<https://doi.org/10.1007/978-3-030-85965-7>

© The Editor(s) (if applicable) and The Author(s), under exclusive license to Springer Nature Switzerland AG 2022

This work is subject to copyright. All rights are solely and exclusively licensed by the Publisher, whether the whole or part of the material is concerned, specifically the rights of translation, reprinting, reuse of illustrations, recitation, broadcasting, reproduction on microfilms or in any other physical way, and transmission or information storage and retrieval, electronic adaptation, computer software, or by similar or dissimilar methodology now known or hereafter developed.

The use of general descriptive names, registered names, trademarks, service marks, etc. in this publication does not imply, even in the absence of a specific statement, that such names are exempt from the relevant protective laws and regulations and therefore free for general use.

The publisher, the authors and the editors are safe to assume that the advice and information in this book are believed to be true and accurate at the date of publication. Neither the publisher nor the authors or the editors give a warranty, expressed or implied, with respect to the material contained herein or for any errors or omissions that may have been made. The publisher remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.

This Springer imprint is published by the registered company Springer Nature Switzerland AG
The registered company address is: Gewerbestrasse 11, 6330 Cham, Switzerland

Preface

1. It is commonly admitted that grouting of existing masonry building elements has a merit to completely respect the initial form of the element to be repaired or strengthened, while improving its resistance and integrity. In the specific case of cultural heritage structures, the respect of the “monumentic” value of the form is of particular interest. That is why, grouting is accepted also in fissured monolithic architectural members, as well as in detached and cracked mosaics or frescoes or surface decoration jointing mortars and plasters; hence the broader significance of this method of structural intervention of existing masonry structures.

This book has a clearly practical scope: to assist the person in charge to design and apply such grout mixes. It is however important to note that masonry grouting is a rather delicate method of structural intervention. Strength improvement is achieved only if grouts of appropriate properties reach the fine discontinuities (voids and microcracks) of the main mass of masonry; simple filling of large voids and cracks is not sufficient. That is why in several cases, masonry grouting was reported to be ineffective, due to grout mixes:

- unable to *penetrate* into finer discontinuities, or
- *not fluid* enough, or
- excessively bled or segregated (i.e., deprived of *stability of the grout*).

That is why, grout-mix-design cannot be carried out by means of rough empirical rules: The number of intervening parameters and their nature do not allow such a solution. Consequently, in order to serve its practical scope, this book should describe in detail the aforementioned performances of a correct grout, in relationship with the internal structure of the masonry. The extent of such descriptions, however, and the necessary scientific handling of the related analysis should not be considered as an unnecessary sophistication; on the contrary, it is presented in a way to help a better understanding of the related phenomena, thus contributing to the best application of this strengthening method.

By its scope, the book is addressed to a rather large audience, such as:

- Structural engineers
- Material engineers
- Chemists
- Architects
- Construction contractors
- Students in the respective disciplines
- Archaeologists specializing in restoration of monuments may also find an interest in reading a good part of this book.

2. The book attempts to contribute toward to a holistic methodology for the mix-design and application of hydraulic grouts,
 - taking into account their injectability (as well as their strength and durability),
 - considering the conditions of the masonry to be repaired or strengthened, and
 - having in mind the targeted properties of masonry after its grouting.

To this end, the comprehensive concept of injectability is first analyzed as the resultant of three grout performances:

- Penetrability, the capacity of the grout to pass through the effective finest width of discontinuities (voids, microcracks, interfaces, joints),
- Fluidity, the capacity of the grout to overcome lateral frictions and to flow up to lengths larger than the distance of consecutive grout tubes,
- Stability, the capacity of the grout to avoid harmful bleeding and segregation along its flow or when in its final place.

Regarding the conditions of the existing masonry, a practical expression of the permeability of its mass is introduced, by means of the concept of nominal width (W_{nom}) of its fine discontinuities affecting its compressive strength.

The required strength of the grout is roughly estimated by means of calibrated empirical formulae, based on the targeted after grouting strength of the masonry. Finally, durability issues are discussed, depending on both environmental conditions and chemical properties of the constitutive materials of the masonry. Based on these concepts, the book describes decision-making methods, resulting in the quantitative composition of the appropriate grout. Due to the multi-parametric nature of the problem, it is obvious to refer also to several preliminary tests, in order to face the inevitable uncertainties accompanying the entire procedure. However, the rationality of the followed methodology insures the rapid convergence of the whole procedure.

The book is concluded with a long chapter, offering practical recommendations for the execution of grouting, together with indispensable quality assurance procedures.

3. A short presentation of the contents of this volume may assist the reader in understanding various aspects of the conceptual design and execution of grouting, as well as in better organizing the reading of the book.

Chapter 1 is an *Introduction* assisting the reader in understanding basic issues of the grouting technology. First, the categories (simple, binary, ternary) of grouts are presented in combination with examples of their use. Subsequently, the main performances required from a hydraulic grout are enumerated; thus, the corresponding design parameters of a grout mix become clear. A design procedure is then described, with reference to the relevant parts of the book, where the reader will find detailed assistance. Finally, it is reminded that an experimental verification of the performances of the “trial mix” has to be carried out in laboratory, and in all cases in situ, during pilot grout preparation and application.

Chapter 2 deals with the first component of injectability, i.e., the *penetrability* of the grains of the grout through the effective finest width W_{nom} of masonry discontinuities (voids, microcracks, interfaces, joints). As it is known, grouting is intended to fill voids, fissures, and open joints of the masonry as a system, producing a “dendrite” (a three-dimensional skeleton), directly contributing to the strength of the masonry as a whole. However, to do so, the grout should be able to pass through the “narrowest” possible width of such discontinuities, in order to reach the maximum possible internal volume of masonry and open joints, avoiding most of possible blockages. In the specific case of three-leaf masonries, the most decisive result of the grouting is expected to be the strengthening of the bond along the interfaces between the external layers and the infill; the rather small voids, as well as pre-existing fissures along these interfaces, have to be penetrated.

In this chapter, the penetrability of hydraulic grouts is discussed, and relationships between (i) two characteristic diameters of the grains of the solid phase of the grout and (ii) the nominal minimum width of fissures and voids of the structure to be injected are proposed. Furthermore, the beneficial role of replacing part of the cement or hydraulic lime with ultrafine materials in order to improve penetrability is presented, and related criteria are proposed. Extensive experimental verifications of the proposed quantitative models are finally offered.

Chapter 3 refers to *fluidity*, i.e., the second component of injectability of the grout: The grout should be able to easily flow along the sinuous paths of internal interconnected discontinuities, up to a distance larger than the distance between consecutive grout tubes. To this end, appropriate water-to-solid ratio (W/S), superplasticizer content (SP), and mixing technique should be selected. A new practical (but scientifically significant) fluidity measurement is proposed (the fluidity factor test—FFT); thus, a “fluidity factor” is defined. It is proved that the follow-up of this factor as a function of the water-to-solid ratio may reveal fundamental characteristics of the grout composition under design.

The influence of the mixing method and superplasticizer on grout’s fluidity is also experimentally studied. The chapter concludes with a case study to highlight the practical use of the proposed test.

Chapter 4 deals with the final component of grout's injectability, i.e., the *stability* of the suspension against excessive bleeding and segregation. The grout should keep its homogeneity up to its setting, as much as possible. When the bleeding remains lower than a certain limit, the grout can be used; otherwise, the grout may be unable to flow in and adhere to the internal surfaces of the discontinuities. Similarly, because of inadequate internal cohesion, larger solid particles of the grout may quickly settle, resulting in segregation phenomena, i.e., creation of a non-homogeneous layered structure of the mix. Excessive bleeding and segregation may produce blockage of the flow and sudden dangerous increase of the pressure.

The most prevailing parameters shaping stability characteristics are water content and percentage of ultrafine materials. After a brief literature survey, an oversimplified predictive model of bleeding is firstly proposed and then its validity is confirmed using the results of an experimental study. The role of superplasticizers is also discussed. In both cases, with and without superplasticizer, semi-empirical formulae are proposed, that are useful for the design of a grout composition. Finally, the chapter presents experimental results demonstrating the role of water and superplasticizer content in the appearance of segregation; some empirical formulae are also proposed for the estimation of the critical water content initiating segregation.

Chapter 5 describes the categories of possible internal discontinuities of masonry; it is because of such discontinuities (pores, local interface detachments, local slidings, cracks) that masonry strength may be reduced. The filling of these discontinuities by means of an appropriate grout may increase masonry strength, provided that the grout was able to penetrate the body of masonry, to reach most of these discontinuities and flow along each of them. In order to decide the necessary "penetrability" capacity of the grout, a rough evaluation of a *critical value* " W_{nom} " of the opening of these discontinuities of masonry is needed.

This chapter examines several possibilities of quantification of such a representative opening value for several categories of masonry. Finally, an easy to apply practical approach of "opening classes" is proposed, and relevant examples are given. Thus, for each specific case, the selection of grout solids' grading is facilitated, in order to satisfy penetrability requirements established in Chap. 2.

Chapter 6 deals with grout-mix-design issues related to the targeted *strength* of the masonry to be grouted. Only two parameters enter the discussion: targeted $f_{wc,s}$ -value and corresponding required $f_{gr,c}$ -value. The chapter explores how a range of required $f_{gr,c}$ -values suffices to be related to a targeted $f_{wc,s}$ -value. This loose correlation is due to the fact that grout-to-stone bond properties are shaping the final structural behaviour of grouted masonry. Thus, tensile rather than compressive strength of the grout is the relevant parameter. Besides, dehydration of grout entering the masonry takes place; consequently, some additional rules regarding mix-composition are respectively derived.

Finally, several empirical relationships are offered predicting masonry compressive strength before and after grouting. Obviously, among the grout compositions resulting in $f_{gr,c}$ -values within the required strength range, those mixes will be retained respecting the other required performances.

The chapter ends with a long Appendix presenting detailed strength results (both tensile and compressive) for several grout compositions, described in the literature.

Chapter 7 is related to *durability* issues. Physical effects are considered first, referring to the consequences of water introduced in masonry by the grouting (freezing and dissolution of soluble phases). Subsequently, chemical effects are considered, such as sulfate reactions, alkali–silica reactions, and possible chlorides' attack and leaching. The chapter ends with a brief presentation of the literature results of durability tests and with a guide for the selection of binders vs. durability.

Chapter 8 refers to some inevitable *contradictory* requirements of a grout, especially related to ultrafines' content (penetrability against fluidity), superplasticizer's content (fluidity against stability), type and content of binders to achieve sufficient bonding with masonry materials, without however imparting to the masonry disproportionately high stiffness (strength against ductility) and without jeopardizing durability (strength against durability) or level of grouting pressure to avoid local rupture of very low masonry strength.

Optimization of grout performances is needed in most cases. To this end, a simple first procedure is proposed following a step-by-step selection of mix-design parameters (Sect. 8.2). First, the type of binder is selected, based on strength and durability demands. An appropriate percentage of fines is then selected, based mainly on penetrability criteria, in combination with strength and durability aspects as well. Using experimental results already presented in Chaps. 2–6, diagrams combining penetrability, fluidity, stability, and strength characteristics vs. W/S ratio are traced. Thus, a “usable” area of water content appears; its compatibility with the required grout strength range will be checked. Normally, several satisfactory solutions are thus found. Otherwise, the necessary correcting measures are discussed in the chapter for each specific case, mainly by means of increased percentages of fines and addition of superplasticizers. This way, the rationality of the proposed methodology is understood. Thus, the designer is in better position to handle the final design of the grout, by means of a better knowledge of the interplay of the intervening numerous parameters.

In Chap. 9, the scientific approach followed in this book finds its justification: The rational and detailed examination of all properties of a grout offers now the possibility to follow a practical step-by-step procedure of mix-design, permitting to handle numerous parameters in a logical sequence. Thus, Chap. 9 contains more practical guidelines for the mix-design of grouts used in masonry strengthening. The guided use of *Tables* and *empirical formulae* presented in Chaps. 2–7 greatly facilitates the selection of (i) the type of binders and the final grading of the solids, (ii) the minimum acceptable fluidity factor, depending on the finest discontinuity width class (W_{nom}), (iii) the zero-bleeding and the critical-bleeding (W/S) expressions (with or without superplasticizers), as a function of the calculated average specific surface S_A of the solid phase, and (iv) the limit value W/S against segregation. Subsequently, a practical procedure for the selection of the final (W/S) ratio of the mix is described, respecting all the aforementioned limits. Corresponding remedy measures are presented in case such a complete respect is not feasible. Moreover, for masonries of minor historical importance and with representative $W_{\text{nom}} \geq 0.25$ mm, a Table is offered, containing

approximate compositions of grouts for four different required grout strength ranges. Experimental verification of the required grout performances will be in any case necessary.

Chapter 10 presents a set of recommendations for the *execution* of grouting, regarding grout tubes installation, description of equipment needed, in situ preparation of the grout, and in situ control of injectability characteristics, as well as in-time evolution of grout's strength. Moreover, methods of in situ checking of injection procedure are presented, together with a description of the data that should be recorded during grouting operations and their evaluation.

The chapter concludes with the assessment of the efficiency of grouting; overall quality management is finally described, together with a detailed presentation of laboratory and in situ nondestructive control tests.

A final observation may be needed here.

To a not yet experienced reader, the described procedure for the design of a correct grout may seem too long. But it should not be forgotten that the final product aimed at by the design, depends on 6 parameters: penetrability, fluidity, bleeding, segregation, strength, and durability—some of them being contradictory to each other, and thus needing optimization. Mathematically *thinking*, it is expected that the solution of a system of 6 equations with 6 variables is not a short procedure; besides, after appropriate modifications, the system should be solved several times, in order for an overall optimum solution to be achieved. With this analogy, the proposed relatively long procedure for grout design may be better justified. Without such a disciplined method, the design may become chaotic.

Obviously, experienced designers will continue employing their own design method; but it is believed that, even experienced designers, may better recognize the nature of some phenomena, thanks to the preceding analysis.

In conclusion, this book may be considered both as a *rational synthesis* and as a *practical guide*.

Athens, Greece

Androniki Miltiadou-Fezans
Theodosios P. Tassios

Acknowledgements

The authors express their gratitude to Anna Kalagri, M.Sc., Chemical Engineer and Conservator of Art, for her continuous assistance with the experiments and the graphics of this book, as well as for her assistance regarding durability matters and, above all, for her critical reading of the entire book.

Thanks are also due to Sophia Anagnostopoulou, M.Sc., Chemical Engineer, Martha Savvidou, M.Sc., Chemical Engineer, and Panagiota Psymogerakou, M.Sc., Civil Engineer, for their help with the experiments and the graphics of this book. The assistance of Michalis Delagrammatikas, M.Sc., Chemical Engineer, regarding durability-related matters is also acknowledged.

Similarly, thanks are due to Euthymia Delinikola, Architect Restorer, and to Fotios Fytilis, Architect, for their kind contribution in the preparation of some of the graphics.

A considerable amount of experimental data included in this book is due to the research works of (i) the Laboratory of Restoration Materials and Techniques of the Directorate for the Restoration of Byzantine and Post-Byzantine Monuments (1995–2004) and (ii) the Laboratory of Building Materials of the Directorate for Technical Research on Restoration (2004–2007) of the Hellenic Ministry of Culture and Sports, carried out for the structural restoration of various monuments in collaboration with several Services of the Hellenic Ministry of Culture and Sports, such as: the Acropolis Restoration Service, the Directorate for the Restoration of Byzantine and Post-Byzantine Monuments, the Directorate for the Conservation of Ancient and Modern Monuments, and the 1st Ephorate of Byzantine Antiquities. We gratefully acknowledge the kind contribution of their scientific and technical Staff.

Particular thanks are due to the Acropolis Restoration Service and the Committee for the Conservation of the Acropolis Monuments, the Ephorate of Antiquities of West Attica, and the Ephorate of Antiquities of Chios of the Hellenic Ministry of Culture and Sports for their kind permission to publish photographs of structural and decorative elements strengthened with grouting, belonging to some very well-known monuments, namely the Parthenon Opisthodomos of the Acropolis of Athens, the Byzantine Monastery of Daphni in Attica, and the Byzantine Church of Panagia Krina in Chios Island. It has to be noted that the rights on the depicted monuments

belong to the Hellenic Ministry of Culture and Sports (Law 3028/2002)/ Hellenic Organization of Cultural Resources Development. The aforementioned monuments are under the responsibility of the Ephorate of Antiquities of the City of Athens (Acropolis), the Ephorate of Antiquities of West Attica (Daphni Monastery) and the Ephorate of Antiquities of Chios Island (Panagia Krina), respectively.

The authors acknowledge with gratitude the scholars who kindly agreed to reproduce in this book part of their published or unpublished material: Prof. Giorgio Macchi and Dr. Simone Ghelfi; Nikolaos Delinikolas, Architect Restorer; Prof. Elizabeth Vintzileou and Dr. Vassiliki Pallieraki; Dr. Xavier Derobert and Dr. Philippe Côte ; Prof. Ioanna Papayianni; Prof. Maria Rosa Valluzzi; Prof. Antonella Elide Saisi; Prof. Charalambos Mouzakis; Prof. Mojmir Uranjek and Prof. Violeta Bokan-Bosiljkof; Dr. Filipp Van Rickstal; Alkimos Papatthanasiou, M.Sc., Structural Engineer; and Aris Velissarios Raptis, Architect.

Similarly, thanks are due (i) to Dr. Anna Melograni, Coordinatore della Redazione of *Bollettino d' Arte*, Ministero per i Beni e le Attività Culturali of Italy, for the permission to reproduce some graphics regarding the grouting intervention in the Pisa Tower, as well as to Antonella d' Aulerio and the Università Iuav di Venezia, Archivio Progetti, Fondo Studio Tecnico prof. ing. Giorgio Macchi, dott. ing. Stefano Macchi, for providing us with high-definition scans of some of the Pisa Tower graphics, (ii) to Prof. I. Papayianni, Associate Prof. M. Stefanidou, and Dr. V. Pacht (eds) of the Proceedings of HMC2016, for their permission to include in this book our paper published in the Proc(s) of HMC2016, as well as (iii) to Prof. J. Jasienko (ed.) of the Proceedings of the 8th Inter. Conf. SAHC 2012 for his permission to reproduce in this book a graphic of a paper included in the Proc(s) of 8th SAHC 2012.

Special thanks are finally due to the colleague Gerard Fezans for his continuous support and encouragement, as well as for his talented representation of many diagrams and graphics of the book.

Contents

1	Introduction	1
1.1	The Significance of the Subject	1
1.2	Categories of Grouts for Masonries	2
1.3	Basic Data Influencing the Design of a Masonry Grout	4
1.4	Main Performances of a Hydraulic Grout	4
1.5	Design Procedure	5
1.6	Practical Guidance for In-Situ Grouting Application Methodology	7
	References	7
2	Penetrability	13
2.1	Introduction	13
2.2	Literature Survey	15
2.2.1	Significance of Penetrability and Relevant Tests for Its Control	15
2.2.2	Maximum Grain Size Criterion	20
2.2.3	Criterion for the Grading of the Coarser Grains	22
2.2.4	Means to Improve Penetrability	24
2.3	Simplified Model and Additional Experimental Data	26
2.4	Calibration	30
2.5	Practical Means to Improve Penetrability of Hydraulic Grouts	35
2.5.1	A Simple Analytical Model	35
2.5.2	Experimental Verification	37
2.6	Conclusions Regarding the Penetrability Grading Criteria for the Grout's Solid Phase	38
2.7	Estimation of a W_{nom} -value	39
	References	40

- 3 Fluidity** 45
 - 3.1 Introduction 45
 - 3.2 Literature Survey 46
 - 3.2.1 Significance of Fluidity 46
 - 3.2.2 Relevant Tests for the Control of Fluidity (The Flow Cone Test) 47
 - 3.2.3 Fluidity Factor Test (FFT) 53
 - 3.3 Further Significance of the Concept of Fluidity Factor—Acceptable Lower Fluidity Factor Values 58
 - 3.4 Effects of Mixing Method on Fluidity 62
 - 3.5 Effect of Superplasticizers 64
 - 3.6 A Case Study of Practical Use of the Fluidity Factor 66
 - 3.7 Conclusions 67
 - References 68

- 4 Stability** 73
 - 4.1 Introduction 73
 - 4.2 Literature Survey 75
 - 4.2.1 Main Parameters Influencing Stability 75
 - 4.2.2 Main Tests to Measure Stability 77
 - 4.3 An Oversimplified Predictive Model of Bleeding 85
 - 4.4 Experimental Investigation on Bleeding 88
 - 4.4.1 Bleeding of Grouts Without Added Superplasticizer 88
 - 4.4.2 The Role of Superplasticizers 95
 - 4.5 Segregation 102
 - 4.5.1 In-Time Modification of Grading of an Unstable Grout 102
 - 4.5.2 In-Space Differentiation of Grading 104
 - 4.5.3 A Simple Analytical Model 104
 - 4.5.4 Practical Criterion of Segregability 106
 - 4.5.5 Cohesiveness Index 108
 - 4.6 Conclusions 110
 - References 111

- 5 Guidelines for the Estimation of W_{nom}** 115
 - 5.1 Introduction 115
 - 5.2 Information on Existing Internal Discontinuities 119
 - 5.3 Quantification Attempts 123
 - 5.4 Practical Approach 124
 - References 127

- 6 Strength-Related Data of Grouts** 129
 - 6.1 Introduction 129
 - 6.2 In Situ Modifications of the Grout After the Injection 130
 - 6.2.1 Dehydration of Grouting Entering the Masonry 130

6.2.2	Measures Against the Dehydration	131
6.3	Grout Strength Versus Masonry Strength Required	131
6.3.1	Introduction	131
6.3.2	Estimation of the Strength of Existing Stone-Masonry Before and After Grouting	132
6.4	Expected Strengths of Grouts	137
6.4.1	Introduction	137
6.4.2	The Main Parameters Influencing the Strength of the Grout	137
6.4.3	Experimental Checking	139
6.4.4	Indicative Strength Values of Grouts	140
6.5	Grout-to-Stone Bond Properties	147
6.6	Selection of a Required $f_{gr,c}$ -range, for Targeted f_{wc} -values	151
6.7	Shrinkage	155
	Appendix: Data Regarding Grouts Compressive and Tensile Strength in Function of the Water to Solids Ratio	156
	References	171
7	Durability	177
7.1	Introduction	177
7.2	Physical Effects	177
7.2.1	Water Introduced During Grouting	178
7.2.2	Fluctuation of Moisture	179
7.3	Chemical Effects	179
7.3.1	Sulphate Reactions	179
7.3.2	Alkali-Silica Reaction (ASR)	181
7.3.3	Chlorides	181
7.3.4	Leaching	182
7.4	Brief Presentation of Main Literature Results on Grout's Durability Testing	183
7.5	Guidance for the Grout Design Versus Durability	184
	References	188
8	Optimisation of Grout Performances	191
8.1	Introduction	191
8.2	The Interaction Between Design-Parameters	193
8.3	Increase of Fines to Improve Compatibility Between Stability and Fluidity	195
8.4	Increase of Fines to Improve Stability Itself	197
8.5	Modifications to Obtain a Minimum Tensile Strength	199
8.6	Addition of Superplasticizer	200
8.7	Conclusion	202
	References	202

9 Practical Guidelines for the Mix Design of Grouts in Masonry

Strengthening 205

9.1 Selection of Binders 206

9.2 Selection of a W_{nom} -value 206

9.3 Checking the “Fineness” of the Binders’ Mixture 206

9.4 Additional Ultrafine Materials 207

9.5 Expected Fluidity Factor and Minimum Water-to-Solids Ratio 208

9.6 Maximum Water-to-Solids Ratio to Ensure Stability 209

9.7 Experimental Examination of the Candidate Composition 210

9.8 Early Critical Bleeding 214

9.9 Strength Evaluation 215

9.10 Possible Simplification 215

9.11 Worksite Conditions 215

References 219

10 Practical Recommendations for the Execution of Grouting 221

10.1 Introduction 221

10.2 Preparation of Masonry and Installation of Injection Tubes 222

10.2.1 Masonry Survey 222

10.2.2 Cleaning of Loose Material and Sealing of Cracks and Voids 223

10.2.3 Drilling the Holes—Grid of Injection Tubes 225

10.2.4 Cleaning of Drilled Holes 229

10.2.5 Installation of Injection Tubes 231

10.2.6 Installation of Fine Injection Tubes in Specific Cases 235

10.3 Main Characteristics of In Situ Grouting Equipment 237

10.3.1 Mixer 237

10.3.2 Agitator 240

10.3.3 Grouting Pump 240

10.3.4 Grout Pipe Lines 241

10.3.5 Grout Recorder 242

10.4 Preparation of Grout and Execution of Injections 242

10.4.1 Mixing Procedure 242

10.4.2 Injection Procedure 243

10.4.3 Finishing of the Masonry Injected Face 247

10.5 On-Worksite Checking of the Prescribed Grout Design Data 250

10.5.1 Pilot Production of Grout in the Worksite 250

10.5.2 Pilot Masonry Application of Grouting 252

10.6 Quality Control of the Grout and of the Injection Procedure During the Execution of Works 253

10.6.1 Visual Inspection 253

10.6.2 Checking Grout Characteristics 254

10.7 Final Report of the Execution of Injections 261

10.8	Assessment of the Grouting Effectiveness After the Completion of the Works	264
10.8.1	Core Taking	265
10.8.2	Endoscopy	265
10.8.3	Sonic/Ultrasonic Methods	267
10.8.4	Radar Technique	272
10.8.5	Other Non-destructive Methods	275
10.8.6	Structural Dynamic Measurements	277
	References	278

Notations

A	Area of the cross section of the nozzle
b	Normalized bleeding value or bleeding capacity
B	Height of bleed water
C	Cement
c	Grout-to-stone cohesion (grout-to-stone shear bond strength under zero normal stress)
C_v	Cement volume
C.I.	Cohesiveness index
d	Diameter of grains
d_v	Diameter of monogranular ultrafine material
d_{ch}	The equivalent diameter of the “channel” (the void)
d_{85}	Diameter of the grains of a granular material (of the solid phase of a grout), corresponding to 85% passing
d_{99}	Diameter of the grains of a granular material (of the solid phase of a grout), corresponding to 99% passing
d_{100}	“Maximum” diameter of the grains of a granular material (of the solid phase of a grout)
D_{15}	Diameter of the grains of a soil or other granular medium to be injected, corresponding to 15% passing
DSF	Densified silica fume
f_{bc}	Compressive strength of blocks
$f_{gr, c}$	Compressive strength of grout
$f_{gr, t}$	Tensile strength of grout
$f_{gr, s}$	Shear resistance of the grout
$f_{gr, b, t}$	Grout-to-stone tensile bond strength
$f_{gr, b, s}$	Grout-to-stone shear bond strength
f_{mc}	Compressive strength of mortar
$f_{wc, requ.}$	The required compressive strength of the masonry after strengthening
$f_{wc, 0}$	Estimated compressive strength of masonry before intervention
$f_{wc, s}$	Estimated compressive strength of masonry, after strengthening
$f_{wc, e}$	Compressive strength of the external masonry leaf

$f_{wc, i}$	Compressive strength of the infill
$f_{wc, i, s}$	Compressive strength of the infill after grouting
f_0	A reduction of masonry strength due to the inhomogeneity of construction, depending on non-orthogonality of blocks
f	Fines (ultrafines)
f_m	Mass percentage of fines (ultrafines)
f_{mp}	Minimal mass percentage of ultrafines to replace a part of the basic binder, in order to ensure penetrability
f_v	Volume percentage of ultrafines
f_{vp}	Minimal volume percentage of ultrafines to replace a part of the basic binder, in order to ensure penetrability
FFT	Fluidity factor test
F_l	Fluidity factor
$\max F_l$	Maximum possible fluidity factor value (for a given composition of solids) under stable conditions
$\min F_l$	Minimum value of fluidity factor for a grout (with appropriate grain penetrability) to be injectable through a sand column with nominal lower value of widths of voids equal to “ W_{nom} ”
G_{gr} and G_w	Weight of the injected grout and initial weight of the single leaf wall, respectively
h_0	Height of the initial specimen of the grout at starting time t_0
h_w	Height of bleed water at prescribed intervals
H	Normalized height of bleeding
HT	High turbulence mixing
IE	Instability estimator
IE_{crit}	Lowest acceptable level of instability
k	Permeability coefficient
k_1 -variables	Expressing the planeity of blocks’ sides (k_1); the filling of joints by mortar (k_2); and the visible cracks and on mortar and block/mortar detachments (k_3)
k_0	Ratio of the volume of mortar to the volume of masonry (one-leaf masonry)
ℓ	Total length of the grouted “channel”
L	Lime
n	Numerical factor larger than unity, to compare W_{nom} and d_{85} (Chap. 2)
n	“Equivalent number” of solid cubes, with an average width of “d”
n	Ratio of the volume of grout embodied to the masonry, normalized to the total volume of the mortar (Chap. 6)
NHL	Natural hydraulic lime
P	Pozzolan
P_{max}	Maximum grouting pressure
Q	Volume of the grout (to pass through the nozzle of a Marsh cone)
r_{32}	Volume percentage of initial cement “retained” on 32 μm
R_{32}	Volume percentage of blend material retained on 32 μm

S_A	Calculated average specific surface of a blended material
S_b	Specific surface Blaine
SP	Superplasticizer percentage
SF	Silica fume
SE	Santorini earth
S_v	Solid volume
S	Solid mass
s_u	Critical slip leading to maximum shear bond resistance
t_f	Flow time through the nozzle of a Marsh cone
$t_{500\text{ml}, d = 4.75}$	Flow time of 500 ml out of 1000 inserted in the Marsh cone with a 4.75 mm nozzle diameter
t_0	Thickness of intergranular adsorbed water
T_{36}	The time the grout takes to reach the top of the sand column (of a height of 36 cm)
US	Ultrasound dispersion mixing
UF	Ultrafines
V	The velocity of flow
V_0	Variable expressing the “permeability” of the building mortar and the infill material of masonry
V_c	Volume of cement
V_{ext}	Volume of the external leaves of masonry
V_m	The volume of mortar
V_w	Volume of bleed water
V_i	The volume of the initial infill material within the entire masonry
$V_{i, gr}$	Initial volume of the grout at the beginning of bleeding test
V_w	The volume of the entire masonry wall
W	Water mass
W_i	Water to solids ratio
W_v	Water volume
W/C	Water-to-cement ratio by mass
W/S	Water-to-solid ratio by mass
W_v/S_v	Water-to-solid ratio by volume
W_{nom}	Nominal lower value of the aperture of fissures or orifices to be injected
$W_i\text{-values}$	Values of the aperture of fissures or orifices to be injected
$(\frac{W}{S})_{0, bl}$	The minimum water-to-solid ratio able to initiate bleeding
$(\frac{W}{S})_{0, bl, SP}$	The minimum water-to-solid ratio able to initiate bleeding, in the case the grout contains superplasticizer
$(\frac{W}{S})_{0, f}$	The minimum water-to-solid ratio able to initiate flow
$(\frac{W}{S})_{bl, cr}$	Water-to-solid ratio leading to 5% bleeding
$(\frac{W}{S})_{bl, cr, SP}$	Water-to-solid ratio leading to 5% bleeding, in the case the grout contains superplasticizer
$(\frac{W}{S})_{sand.-col.}$	Water-to-solid ratio for which the grout starts to be able to be injectable in the sand column

$\left(\frac{W}{S}\right)_{segr.}$	Water-to-solid ratio for which the grout starts to exhibit segregation
$\left(\frac{W}{S}\right)_{u, f}$	An ultimate value of water-to-solid ratio, which practically results in the maximum possible fluidity factor (for a particular composition of solids) without instability effects
z	An Instability estimator (IE)-related quasi-constant
α	Rate factor
β	Coefficient reflecting the substrate type (Chap. 6)
$\alpha, \beta, \gamma, \delta$	Rheology-related constants, depending on the roughness of the walls and the form of the cross section of the channel, as well as on rheological properties of the grout (Chap. 3)
δ	Constant
$\delta = t_e/t_i$	Ratio of the respective thickness of external leaf and infill (in case that the external leaves have the same thickness)
$\delta_{e1} = t_{e1}/t_i$	Ratio of the respective thickness of external leaf “1” and infill
$\delta_{e2} = t_{e2}/t_i$	Ratio of the respective thickness of external leaf “2” and infill
ΔH	Bleeding capacity (settlement per unit original height)
Δf_0	Reduction of the masonry inhomogeneity factor (counteracting the severity of the initial f_0 -value included in the expression of $f_{wc, 0}$)
Δf_m	Additional quantity of fines
Δw	Additional quantity of water
Δp	Pressure loss along a length “ ℓ ”
ζ	Constant
η	Plastic viscosity
λ	Correction factor
λ	Mortar-to-stone bond factor
λ_1, λ_2	Numerical factors
λ_3	A constant, reflecting the lowest acceptable level of instability IE_{crit}
λ_e, λ_i	Correction factors in order to take into account the interaction between the external leaves and the infill
λ_i -variables	In function to the type of the wall (one-leaf, two-leaf, or three-leaf)
μ	Water equivalence constant of superplasticizer
μ_{max}	Maximum friction coefficient
μ_{res}	Residual friction coefficient
ξ	A factor expressing the adverse effect of thick mortar joints
ρ_{ms}	Average density of the solids
ρ_w	Water density
ρ_{mf}	Average density of fines
ρ_b	Density of the basic binder
σ	Normal stress acting on a sheared interface
τ_0	Yield stress of a fluid
ω	Equivalent W/S, accounting for SP